GELEE - 2343





Collection: Pret a porter

Range: Touch Colour: Black

SUBSTANCES	SIZE MACHII	NE DIREC	VERSO	MINIMUM ORDER	PACKING
195gsm	Foglio 72cmx102cm	102	Nero	125Fogli	Foglio
110gsm	Foglio 72cmx102cm	102	Nero	125Fogli	Foglio

Data sheet

Printing techniques

Offset printing: good Screen printing: good Hot stamping: excellent Dry debossing: excellent Coating: excellent UV coating: excellent Print oxidation: 1

Abrasion resistance

Abrasion resistance: alta
Wet strength: medium/high

Notes for printing and inks

For better results in offset printing, we advise you to avoid high piles and allow to dry thoroughly before proceeding to the subsequent processing phases. We recommend using high-quality oxidising or quick-set inks. If the offset machine is equipped with an IR dryer, we recommend using it.

PRINT OXIDATION

Hot stamping in gold, silver or metals on black paper can generate oxidation or marbling effects in particularly hot and humid weather conditions or if unsuitable films are used.

In such cases, we recommend using NO-OX (antioxidant) material available on request

CERTIFICATIONS

SUBSTANCES



PH





LONG LIFE

EN 71/3

FSC www.fsc.org psc. coststoos





195gsm

110gsm

ECF

ECF

_

_

.

- .

Legend

present

Partial

_ Absent