



Collection: PrĂŞt-Ă -porter
Gamme: Gold
CouleurOr
Type de gaufrage: GĂ©omĂ©triques
GRAIN: Fibra di carbonio
Grain: 216

GRAMMAGE	FORMAT	VERSE DE MACI	VERSO MINIMUM DE COMMAN	CONDITIONNEMENT
120gsm	Foglio 70cmx100cm	100	Bianco	125Fogli
				Foglio

Fiche technique

Techniques d'impression

Imprimabilit  Offset: optimale
Imprimabilit  S rigraphique: optimale
Imprimabilit    chaud: optimale
Imprimabilit    sec: optimale
Imprimabilit  digitale: optimale
Oxydabilit  d'impression: 0

Notes pour l'impression et l'encre

Pour un meilleur rendement d'impression offset, il est conseill  d viter les hautes piles et de bien laisser s cher avant de proc der avec les phases suivantes du travail. Il est conseill  l'utilisation d'encre oxydatives ou quick-set de haute qualit . Si la machine offset est  quip e d'un dessiccateur IR il est conseill  de l'utiliser.

CERTIFICATIONS

GRAMMAGE



120gsm

ECF

—



—

—



—

—

LÃ©gende

● prÃ©sent

◐ Partiel

— Absent