




Collection: PrĂŞt-Ă -porter
Gamme: Coppers
CouleurCuivre

GRAMMAGE	FORMATVERSE DE MACI	VERSO MINIMUM DE COMMAN	CONDITIONNEMENT
120gsm	Foglio 70cmx100cm 100	Bianco	125Fogli Foglio

Fiche technique

Techniques d'impression

Imprimabilit  Offset: optimale
Imprimabilit  S rigr phique: optimale
Imprimabilit    chaud: optimale
Imprimabilit    sec: optimale
Vernissage: optimale
Vernissage UV: optimale
Oxydabilit  d'impression: 0

R sistance   l'abrasion

R sistance   l'abrasion: media
R sistance   l'humidit : moyenne

Notes pour l'impression et l'encre

Pour un meilleur rendement d'impression offset, il est conseill  d viter les hautes piles et de bien laisser s cher avant de proc der avec les phases suivantes du travail. Il est conseill  l'utilisation d'encre oxydatives ou quick-set de haute qualit . Si la machine offset est  quip e d'un dessiccateur IR il est conseill  de l'utiliser.

CERTIFICATIONS

GRAMMAGE



120gsm

ECF



LÃ©gende

● prÃ©sent

▮ Partiel

— Absent